

Specializing in Fiber, Yarn, Fabric & Apparel Testing  
19 West 36<sup>th</sup> Street, New York, NY 10018

Phone: (212) 947-8391 Fax: (212) 947-8719

ILAC-I.S.O. Certified Third Party Test Report

DATE: February 11, 2009

FILE: PHDPRD.A020409A  
ORDER\PO #: 2009-01

CLIENT: PHD Productions LLC  
5010 Henry Lane  
Hillsborough, NC 27278

ATTN: Patrick Groft

SAMPLE IDENTIFIED BY CLIENT AS:

Pocket Disc Submitted  
Season: Winter  
Manufacturer: Allen Stern  
Style: Sunburst Sports/Classic  
Ref: Toy, Lot #: 2008-05  
Color Ocean Blue W/Multi

TEST PROCEDURE:

TEST RESULTS:

LEAD CONTENT BY FLAME  
ATOMIC ABSORPTION:

- ALL COMPONENTS: < 10 mg/kg (ppm)

CPSIA REQUIREMENTS (16 CFR 1303):

Coating: < 600 ppm  
Substrate: < 600 ppm

TEST SUMMARY: Pass

PHthalates Content  
BY GC/MS:

- DI-N-BUTYLPHthalATE: < 100 ppm  
- BENZYL BUTYL PHthalATE: < 100 ppm  
- DI (2-ETHYLHEXYL)  
PHthalATE: < 100 ppm  
- DI-N-OCTYL PHthalATE: < 100 ppm  
- DIISONONYL PHthalATE: < 1000 ppm  
- DIISODECYL PHthalATE: < 1000 ppm

Signed For The Company By

Adam R. Varley  
Technical Director

MH/02/139



Stacy Sadowy  
Stacy Sadowy  
Quality Assurance Supervisor



Specializing in Fiber, Yarn, Fabric & Apparel Testing  
19 West 36<sup>th</sup> Street, New York, NY 10018

Phone: (212) 947-8391 Fax: (212) 947-8719

## ILAC-I.S.O. Certified Third Party Test Report

DATE: February 11, 2009

FILE: PHDPRD.A020409B  
ORDER\PO #: 2009-01

CLIENT: PHD Productions LLC  
5010 Henry Lane  
Hillsborough, NC 27278

ATTN: Patrick Groft

### SAMPLE IDENTIFIED BY CLIENT AS:

Pocket Disc Submitted  
Season: Winter  
Manufacturer: Allen Stern  
Style: Sunburst Sports/Classic  
Ref: Toy, Lot #: 2008-05  
Color Red/Black W/Multi

### TEST PROCEDURE:

### TEST RESULTS:

LEAD CONTENT BY FLAME  
ATOMIC ABSORPTION:

- ALL COMPONENTS: < 10 mg/kg (ppm)

### CPSIA REQUIREMENTS (16 CFR 1303):

Coating: < 600 ppm  
Substrate: < 600 ppm

TEST SUMMARY: Pass

### PHthalates Content

BY GC/MS:

- DI-N-BUTYLPHthalATE: < 100 ppm  
- BENZYL BUTYL PHthalATE: < 100 ppm  
- DI (2-ETHYLHEXYL)  
PHthalATE: < 100 ppm  
- DI-N-OCTYL PHthalATE: < 100 ppm  
- DIISONONYL PHthalATE: < 1000 ppm  
- DIISODECYL PHthalATE: < 1000 ppm

Signed For The Company By

Adam R. Varley  
Technical Director

MH/02/140



Stacy Sadowy  
Stacy Sadowy  
Quality Assurance Supervisor

